

BONANZA

Type of leather:	bovine
Origin:	European and non-European
Thickness:	mm. 0,9 - 1,00 ± 0,1
Average size:	43-45sqf
Tannage:	chrome salts
Dye:	aniline dye
Finishing:	mixtures of oils, waxes and polyurethane ecological
Appearance:	natural grain with pull-up effect

SPECIFICATIONS*

ANALYSIS	TEST METHOD	UNIT OF MEASUREMENT	RECOMMENDED VALUE
Colour fastness to dry rubbing 50 cycles	UNI EN ISO 11640 UNI EN ISO 11641	Grey scale	3
Colour fastness to wet rubbing 20 cycles	UNI EN ISO 11640 UNI EN ISO 11641	Grey scale	3
Colour fastness to alkaline sweat 20 cycles	UNI EN ISO 11640 UNI EN ISO 11641	Grey scale	3
pH	UNI EN ISO 4045	-	3,5
Tear strenght	UNI EN ISO 3377-1	N	20
Colour fastness to light xenotest	UNI EN ISO 105 B02	Blue scale	3

*All submitted tests results are obtained using official methods on non-manipulated leather. Further tests made after using leather, must be agreed between the producer and the buyer.