

PICASSO

| | |
|-------------------------|----------------------------------|
| Type of leather: | bovine |
| Origin: | European and non-European |
| Thickness: | mm. 0,9 - 1,00 ± 0,1 |
| Average size: | 43-45sqf |
| Tannage: | chrome salts |
| Dye: | aniline dye |
| Finishing: | pigmented |
| Appearance: | two-tone effect |

SPECIFICATIONS*

| ANALYSIS | TEST METHOD | UNIT OF MEASUREMENT | RECOMMENDED VALUE |
|---|--------------------------------------|---------------------|-------------------|
| Colour fastness to dry rubbing 500 cycles | UNI EN ISO 11640 UNI EN ISO 11641 | Grey scale | 4 |
| Colour fastness to wet rubbing 250 cycles | UNI EN ISO 11640 UNI EN ISO 11641 | Grey scale | 3/4 |
| Colour fastness to alkaline sweat 80 cycles | UNI EN ISO 11640 UNI EN ISO 11641 | Grey scale | 3/4 |
| Finish adhesion | UNI EN ISO 11644 | N/10 mm | 2 |
| pH | UNI EN ISO 4045 | - | 3,5 |
| Tear strenght | UNI EN ISO 3377-1 | N | 20 |
| Dry flexing | UNI EN ISO 5402 | Cycles | 20.000 |
| Colour fastness to light xenotest | UNI EN ISO 105 B02 | Blue scale | 5 |
| Flammability | UNI EN 1021-1:2006 | - | No Ignition |
| Flammability | UNI EN 1021-2:2006 | - | No Ignition |
| Cigarette test (California) | TB117 | - | Pass |

*All submitted tests results are obtained using official methods on non-manipulated leather.
Further tests made after using leather, must be agreed between the producer and the buyer